

Colonial Beach

Colonial Beach gives your home the classic look of freshly painted wood and it will continue to look that way because Colonial Beach is manufactured using a proprietary compound that has been specifically formulated for outstanding resistance to adverse weather conditions like wind, rain, snow and damaging effects of ultraviolet light. This formulation also provided outstanding impact resistance and durability.



- Our unique Double 6" clapboard profile looks like freshly painted wood.
- Never needs painting.
- Virtually maintenance free.
- Comes with a full Line of accessories
- Made with the Rich-Lock™ Color System.
- Comes with a Lifetime Limited Warranty including fade and hail Protection.

Colonial Beach provides you with a lifetime of protection for your investments as well as peace of mind for as long as you own your home.

Manufacturer

Materials to be supplied by Continental Manufacturing, 1026 S. Powell Road, Independence, MO 64055

Materials

All of the vinyl siding shall be extruded Poly Vinyl Chloride (PVC) and shall conform to the following requirements established by ASTM Specifications D 3679, developed in cooperation with the industry and published by the American Society for Testing and Materials.

Typical Compound Properties

Tensile Strength: ASTM D638 6,040 psi
Tensile Modulus: ASTM D638 365,000 psi
Flexural Strength: ASTM D790 11,500 psi
Flexural Modulus: ASTM D790 410,000 psi
Izod 73°F Method A 17.0 ft-lb/in

VSI Flammability

Burn Length (0.040 in Bar) ASTM D635 0* IN. Burn Time (0.040 in Bar) ASTM D635 0* Sec
Drop Dart Impact Resistance Procedure A, 73° F ASTM D4226 1.9 in-lb/mil
Drop Dart Impact Resistance Procedure B, 73° F ASTM D4226 4.0 in-lb/mil
Vulcanizate Properties Hardness Instantaneous, D ASTM D2240 83
Thermal Properties HDT Unannealed, 264 psi ASTM D648 162 °F
Coeff of Linear Thermal Expansion ASTM D696 3.6EO in/in/°F

Gloss: plus or minus 5 units, ASTM D3679

Surface Distortion: No Distortion at 105°F, ASTM D3679

Weatherability: No surface or structural defects when tested as per ASTM D3679

Siding Dimensions and Description

Colonial Beach D6, horizontal siding panel, 12 in. wide exposure configured as two 6 in. panels, 12' and 16' 8" length. Thickness 0.044 in. ±0.002 in.

Embossed Wood Grain: Color to match the samples provided.

Interlock: Siding panels are made with post form style lock with positive interlock.

Both ends of the panel are factory cut and notched for overlap.

Weep holes: Small holes under the bottom butt prevent vapor build up and allow accumulated moisture to escape.