

# Chesapeake Bay

- Available in Double 4.5" and Double 4.5"Dutchlap profile.
- Outstanding beauty that will last a lifetime.
- Deep cedar wood grain finish that's perfect for remodeling and new homes.
- The color is actually part of the siding material itself, so nicks and scratches won't show.
- Rugged good looks.
- Timeless design and a solid value.
- Comes with a complete color coordinated range of trims and accessories to add that special finishing touch to your design.
- .042 thickness that retains strength, stability and good looks year after year.
- Virtually maintenance free - never needs painting.
- Superior value and low maintenance performance in all environments



## Manufacturer

Materials to be supplied by Continental Manufacturing LLC, 1026 S. Powell Road, Independence, MO 64055.

## Materials

All of the vinyl siding shall be extruded Poly Vinyl Chloride (PVC) and shall conform to the following requirements established by ASTM Specifications D 3679, developed in cooperation with the industry and published by the American Society for Testing and Materials.

## Typical Compound Properties

Tensile Strength: ASTM D638 6,040 psi  
Tensile Modulus: ASTM D638 365,000 psi  
Flexural Strength: ASTM D790 11,500 psi  
Flexural Modulus: ASTM D790 410,000 psi  
Izod 73°F Method A 17.0 ft-lb/in

## VSI Flammability

Burn Length (0.040 in Bar) ASTM D635 0\* IN. Burn Time (0.040 in Bar) ASTM D635 0\* Sec  
Drop Dart Impact Resistance Procedure A, 73° F ASTM D4226 1.9 in-lb/mil  
Drop Dart Impact Resistance Procedure B, 73° F ASTM D4226 4.0 in-lb/mil  
Vulcanizate Properties Hardness Instantaneous, D ASTM D2240 83  
Thermal Properties HDT Unannealed, 264 psi ASTM D648 162 °F  
Coeff of Linear Thermal Expansion ASTM D696 3.6EO in/in/°F  
Gloss: plus or minus 5 units, ASTM D3679  
Surface Distortion: No Distortion at 105°F, ASTM D3679  
Weatherability: No surface or structural defects when tested as per ASTM D3679

## Siding Dimensions and Description

Chesapeake Bay D4.5 and D4.5 Dutchlap, horizontal siding panel, 9 in. wide exposure configured as two 4.5" in. panels, 12' & 16'8" lengths. Thickness 0.042 in. ±0.002 in.

Embossed Wood Grain: Color to match the samples provided.

Interlock: Siding panels are made with post form style lock with positive interlock.

Both ends of the panel are factory cut and notched for overlap.

Weep holes: Small holes under the bottom butt prevent vapor build up and allow accumulated moisture to escape.